

HYBRID®



Industry's most versatile floor finish

A revolutionary new polymer system formulated with XBF technology that provides the longest lasting finish ever. This self sealing extended wear formula retains film integrity and outstanding gloss even after repeated detergent mopping and burnishing. This finish effectively reduces maintenance and prolongs the time between strippings. Specifically formulated for medium maintenance programs, this product will retain its gloss between burnishings. In high speed programs it greatly reduces the need to frequently use a restorer.

Features

Extended wear formula provides the longest lasting shine possible.
0.0% Free Styrene
Versatile - low to frequent maintenance programs
Self-sealing formation.

Available In

4 - 1 Gal. Bottles Item #66004-00

5 Gal. Pail Item #66005-00

5 Gal. BIB Item #66039-00

55 Gal. Drum Item #66055-00

2 - 1.25 Gal. Quickcoat Item #66059-00

Directions for Use

Recommended for use on all types of resilient tile flooring and properly prepared hard surfaces.

RESTORATIVE MAINTENANCE: Completely remove all old wax, finish and soil from floor surface following strip procedure instructions on Betco stripper label. Floor surface must be clean, dry and free of residue before finish is applied. Rinse with clean water if necessary. Apply finish in uniform, thin to medium coats using a clean synthetic finish mop, microfiber mop or applicator system. Allow each coat to dry thoroughly before applying additional coats, usually 20 - 30 minutes. Elevated temperatures, heavy coats and humidity may extend dry time. A minimum of 4 coats of finish is recommended. Note: This product is a self-sealing finish, however, if tile is old, worn or porous, initially applying 1 - 2 coats of a Betco sealer will enhance gloss and long term performance.

ROUTINE MAINTENANCE: Sweep large debris and dust mop. Damp mop or automatic scrub using a Betco floor cleaner. Buff or burnish the floor to enhance gloss as needed. Use Betco One Step High Speed Cleaner/Restorer to condition the floor and extend the time between top scrub and recoating.

INTERIM MAINTENANCE: Sweep large debris and dust mop. Top scrub the floor using Daily Scrub SC and maroon pad or equivalent to remove the top soiled layers of finish. Floor surface must be clean, dry and free of residue before finish is applied. Apply 1 - 2 coats of finish as directed above.

Please recycle empty containers. Note: Slip resistance meets or exceeds standard, (ASTM D 2047-11) James Machine 0.5 minimum.

Tech Specs

Color (dried film)	Crystal clear
Color (liquid)	White
Coverage	2000 - 3000 square feet/gallon
Fragrance	Mild
Freeze/thaw stability	3 cycles
Gloss (ASTM D 1455-87)	1 coat 85 - 90 2 coats 97 - 98
Heel mark resistance	Excellent
Leveling	Outstanding
pH	8.2 - 8.9
Powdering resistance	Excellent
Warranty	2 years