

UNTOUCHABLE® WITH SRT™



Black mark resistant metal interlocked floor finish

Untouchable with Scuff Resistant Technology SRT is a low odor, black heel mark resistant floor finish that is an exceptional choice for those who want the highest gloss and wear with the least amount of labor. Untouchable with SRT is nonscuffing, durable, detergent resistant and maintains its high gloss with minimal burnishing, a real labor saver. Excellent leveling and low odor make it easy to apply

Features

- Superior black heel mark resistance
- Extremely low odor
- Superior protection for your floor
- Self-sealing

Available In

4 - 1 Gal. Bottles Item #60604-00

5 Gal. Pail Item #60605-00

5 Gal. BIB Item #60639-00

55 Gal. Drum Item #60655-00

2 - 1.25 Gal. Quickcoat Item #60659-00

Directions for Use

Recommended for use on all types of resilient tile flooring and properly prepared hard surfaces.

RESTORATIVE MAINTENANCE:

Completely remove all old wax, finish and soil from floor surface following strip procedure instructions on Betco's 174; stripper label. Floor surface must be clean, dry and free of residue before finish is applied. Rinse with clean water if necessary. Apply finish in uniform, thin to medium coats using a clean synthetic finish mop, microfiber mop or applicator system. Allow each coat to dry thoroughly before applying additional coats, usually 20 - 30 minutes. Elevated temperatures, heavy coats and humidity may extend dry time. A minimum of 4 coats of finish is recommended. Note: This product is a self-sealing finish, however, if tile is old, worn or porous, initially applying 1 - 2 coats of a Betco sealer will enhance gloss and long term performance.

ROUTINE MAINTENANCE:

Sweep large debris and dust mop. Damp mop or automatic scrub using a Betco floor cleaner. Buff or burnish the floor to enhance gloss as needed. Use Betco's One Step High Speed Cleaner/Restorer to condition the floor and extend the time between top scrub and recoating.

INTERIM MAINTENANCE:

Sweep large debris and dust mop. Top scrub the floor using Daily Scrub SC and maroon pad to remove the top soiled layers of finish. Floor surface must be clean, dry and free of residue before finish is applied. Apply 1 - 2 coats of finish as directed above.

Please recycle empty containers. Note: Slip resistance meets or exceeds standard, (ASTM D 2047-11) James Machine 0.5 minimum.

Tech Specs

Coverage	2,000 - 3,000 square feet/gallon
Drying time	20 - 30 minutes
Warranty	2 years
Heel mark resistance	Excellent
Fragrance	Mild
Freeze/thaw stability	3 cycles
Gloss (ASTM D 1455-87)	1 coat 80 - 85 2 coats 97 - 98
Gloss (ASTM D 1455-87)	2 coats 97 - 98
Leveling	Excellent
pH	8.1 - 8.9
Powdering resistance	Excellent
Recoat	Very good
Specific gravity	1.03
Free styrene content	0.0